

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(10) International Publication Number  
WO 2004/006365 A1

(43) International Publication Date  
15 January 2004 (15.01.2004)

PCT

(51) International Patent Classification<sup>7</sup>: H01M 4/86,  
4/88, 8/02

BROERSEN, Bartholomeus, Cornelis (NL/NL); Jan  
Arentsweg 14, NL-1749 HP Warmerhuizen (NL).

(21) International Application Number:  
PCT/NL2003/000492

(74) Agent: VAN WESTENBRUGGE, Andries; Nederland-  
sch Octrooibureau, Scheveningsweg 82, P.O. Box 29720,  
NL-2502 LS The Hague (NL).

(22) International Filing Date: 3 July 2003 (03.07.2003)

(25) Filing Language: Dutch

(26) Publication Language: English

(30) Priority Data:  
1020985 3 July 2002 (03.07.2002) NL


(71) Applicant (for all designated States except US): STICHT-  
ING ENERGIEONDERZOEK CENTRUM NEDER-  
LAND (NL/NL); Westerdinweg 3, NL-1755 LE Petten  
(NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KR, KG, KP, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,  
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,  
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GI, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: ANODE-SUPPORTED FUEL CELL



(57) Abstract: Anode-supported fuel cell, in particular SOFC, where stresses in the anode substrate are compensated for by a stress compensation layer. According to the invention said stress compensation layer is made porous by making a large number of very small openings. These openings are preferably made hexagonal and the thickness of the walls between the openings is minor. An electron-conducting porous layer is applied to the stress compensation layer.

WO 2004/006365 A1

1. The first step in the process is to identify the problem or issue that needs to be addressed. This involves gathering information and understanding the context of the problem.

13

WO 2004/006365

PCT/NL2003/000492

1

Anode-supported fuel cell

The present invention relates to an anode-supported fuel cell comprising an anode support, an anode layer, an electrolyte layer and a cathode layer, said anode support being provided with a stress compensation layer on the side opposite the anode layer.

A fuel cell of this type is disclosed in WO 01/43524. Such a fuel cell consists of layers of different materials with different coefficients of expansion. During the appreciable changes in temperature in the cell, as well as the changes in volume as a result of the chemical reactions that take place in the anode substrate, there is a risk that the latter warps. This makes the production of a cell stack particularly difficult; the deformability and the mechanical strength of such a cell are so low that "furling" straight inevitably leads to fracture.

To avoid this problem, which arises mainly during the first sintering of the anode support, it is proposed in WO 01/43524 to apply a stress compensation layer. This stress compensation layer is on the side of the anode support that is opposite the side of the anode support where the anode is applied. By making the mechanical and shrink characteristics thereof essentially the same as those of the electrolyte layer it is possible largely to prevent warping.

However, it is important that the process in the fuel cell can take place without hindrance. That is to say that it must be possible for transport of both gases and electrons to be able to take place without hindrance.

To this end it is proposed in the abovementioned PCT application to make relatively large openings in the stress compensation layer through which gases are able to move. The openings also serve as contact pressure points for a current collector. Transport of gases must take place through these openings. There is a relatively large distance between the openings which is varied depending on the position with respect to the point at which the gases are introduced. This part of the stress compensation layer is permeable to gas.

This means that stringent requirements are imposed with regard to the accurate positioning of the stress compensation layer with respect to the other parts of the fuel cell and more particularly the current collector. In view of the inaccuracy this means that the holes in the stress compensation layer through which the current collector extends have to be made relatively large.

WO 2004/006365

PCT/NL2003/000492

## 2

The method for the production of such a stress compensation layer is complex. It is proposed, starting from the anode support, to mask certain regions thereon and then to apply the stress compensation layer in some way or other and then to sinter the assembly.

As a result of the large distance between the holes there is the disadvantage that a  
5 uniform distribution of gases, ions and electrons at the location of the anode can no longer be ensured. This applies in particular if the supporting substrate is relatively thin. The aim is for relatively thin components in order to reduce the costs of the materials for such a cell as far as possible.

The aim of the present invention is to avoid the disadvantages described above and to  
10 provide an anode-supported fuel cell with which, on the one hand, the problem indicated above and possible warping of the anode support are prevented and which, on the other hand, can be produced in a simple manner and guarantees a more uniform distribution of ions and electrons.

This aim is realized with an anode-supported fuel cell as described above in that said  
15 stress compensation layer is a porous layer extending without essential interruptions and a porous layer with a thickness of at most 100  $\mu\text{m}$  that is electron-conducting in the operational state is applied to said stress compensation layer on the side away from the anode support.

According to the present invention there are no longer relatively large holes in the  
20 stress compensation layer but this layer extends continuously. The stress compensation layer is provided with a large number of relatively small openings that preferably have a maximum diameter of 1 mm. More particularly, the diameter (converted to relate to a circular opening) is approximately 0.4 mm. Such relatively small openings can have any conceivable shapes, but according to an advantageous embodiment of the invention are  
25 made hexagonal. The distance between the openings is restricted so that the effect of non-uniform distribution described above, especially in the case of thin layers, does not arise. In particular, the distance between adjacent openings, that is to say the "wall thickness" between the openings is less than 1 mm and more particularly approximately 0.3 - 0.5 mm and according to a particularly preferred embodiment approximately 0.4 mm. Surprisingly,  
30 it has been found that when a stress compensation layer of such a construction is used warping of the fuel cell can be prevented. With the stress compensation layer according to the invention it is possible to keep the distance that the gas travels to the electrolyte as small as possible. This distance is preferably less than 800  $\mu\text{m}$ .

WO 2004/006365

PCT/NL2003/000492

3

The stress compensation layer is preferably a zirconium oxide layer.

By applying a further electron-conducting porous layer to the stress compensation layer it is no longer necessary for the actual current collector to be directly in contact with the stress compensation layer or the anode. Such a porous electron-conducting layer, which functions as auxiliary current collector, is preferably a nickel/nickel oxide layer of relatively small thickness of at most 100  $\mu\text{m}$  and more particularly approximately 50  $\mu\text{m}$  at the time of application. This results in a layer thickness of approximately 10 - 20  $\mu\text{m}$  (nickel) after sintering and reduction. As a result of the application of such a further electron-conducting layer the number of contact points through the stress compensation layer can be appreciably increased. The pore sizes of such a porous layer are preferably between 0.2 - 0.6  $\mu\text{m}$  and more particularly are approximately 0.4  $\mu\text{m}$ .

The various components from which the fuel cell is made up can be all components known in the state of the art. The same applies with regard to the method of production of the fuel cell. In general, the anode (including support and electrolyte) will first be sintered at a relatively high temperature, after which the cathode is applied and sintering then takes place at a somewhat lower temperature. However, it is also possible to produce the fuel cell or electrochemical cell according to the invention in a larger number of steps or smaller number of steps. When producing the electrochemical cell in the manner described above, after providing the anode support and applying the anode layer, optional auxiliary layer and electrolyte thereto, the stress compensation layer is applied to the other side of the anode substrate. According to the present invention, this application takes place by means of a printing technique and more particularly by means of a screen printing technique. By this means it is possible to make a very regularly distributed pattern of very small openings with the very small layer thicknesses. Moreover, such a screen printing technique is particularly simple to carry out and it is no longer necessary for certain parts of the anode substrate to be masked and the like. After applying the stress compensation layer using some printing technique or other, the nickel oxide layer or other layer that is porous and electron-conducting after sintering is then applied. The assembly described above can then be sintered at a temperature of approximately 1400 °C. Of course, it is also possible, starting from the anode support, to vary the sequence of the application of the various layers to some extent.

The shape of the small openings in the stress compensation layer that can be obtained by means of screen printing can be any shape known the state of the art. Preferably, the

WO 2004/006365

PCT/NL2003/000492

4

various features are produced in a regular honeycomb pattern.

It has been found that with a cell as described above the problem of warping of the anode support can be solved, whilst, on the other hand, with a simple production method combination of the cell components can easily be achieved and uniform distribution of gases, electrons and ions over the anode support is guaranteed.

The invention will be explained in more detail below with reference to an illustrative embodiment shown in the drawing. In the drawing:

Figure 1 shows, diagrammatically in cross-section, the various layers of the anode-supported fuel cell according to the invention; and

Figure 2 shows a plan view of the stress-compensating layer immediately after this has been applied to the anode substrate.

In Fig. 1 the fuel cell according to the present invention is shown by 1. This fuel cell is indicated in its entirety by 1 and consists of an anode support 2. This anode substrate can be made of any material known in the state of the art, such as porous NiO/YSZ.

The actual anode (auxiliary) layer 3 is applied thereto. Of course, this layer 3 can be omitted. An electrolyte layer is indicated by 4. The cathode, which is indicated by 5, is applied thereto. This is merely diagrammatic and this cathode can consist of a larger number of layers.

The anode support 2 is provided on the other side with a stress compensation layer 6. This is made without large openings and applied to anode support 2, for example by screen printing. Very small openings with a diameter (based on a circle) of 1 mm or less are made during screen printing. This stress compensation layer preferably consists of a material having thermal and mechanical properties corresponding to those of the material of layer 4. That is to say, if stresses arise between substrate 2 and layer 4 during heating or cooling or during chemical reactions precisely the same stresses will arise between substrate 2 and layer 6, as a result of which warping of said substrate is prevented.

A porous electron-conducting layer, such as a layer of nickel oxide which on sintering and reduction is converted to porous nickel is applied to layer 6. The thickness of such a layer is less than 100  $\mu\text{m}$ , preferably approximately 50  $\mu\text{m}$ , at the time of application, so that a layer thickness of 10 - 20  $\mu\text{m}$  results on sintering.

The porosity of layer 6 is preferably 40 %.

Of course, components or various components taken together which have special properties that are produced during the production of the fuel cell described above also fall

WO 2004/006365

PCT/NL2003/000492

5

within the scope of the present invention. That is to say, rights are requested for an assembly consisting of an anode-supported cell provided with a stress compensation layer according to the invention, optionally in combination with the electron-conducting layer applied thereto, both in the green and in the sintered state.

5 A current collector, indicated highly diagrammatically, presses against layer 7.

Fig. 2 shows a plan view of layer 6 after application to layer 2 by screen printing. The very regular hexagonal pattern of the openings extending through layer 6 which link substrate 2 and layer 7 can clearly be seen from this figure.

10 Although the invention has been described above with reference to a preferred embodiment, it will be understood that numerous modifications can be made thereto without going beyond the scope of the present invention as described in the claims.

WO 2004/006365

PCT/NL2003/000492

6

### Claims

1. Anode-supported fuel cell (1) comprising an anode support (2), an anode layer (3), an electrolyte layer (4) and a cathode layer (5), said anode support (2) being provided with a stress compensation layer (6) on the side opposite the anode layer, characterised in that said stress compensation layer (6) is a porous layer (7) extending without essential interruptions and a porous layer with a thickness of at most 100  $\mu\text{m}$  that is electron-conducting in the operational state is applied to said stress compensation layer on the side away from the anode support.
2. Fuel cell according to Claim 1, wherein the electron-conducting layer has a thickness of 10 - 20  $\mu\text{m}$  in the operational state.
3. Fuel cell according to one of the preceding claims, wherein said electron-conducting layer (7) comprises a nickel/nickel oxide layer.
4. Fuel cell according to one of the preceding claims, wherein the stress compensation layer is provided with a regular pattern of holes extending from the substrate to the electron-conducting layer, said holes having an internal opening of at most 1 mm.
5. Fuel cell according to Claim 4, wherein said holes are hexagonal.
6. Fuel cell according to one of the preceding claims, wherein said stress compensation layer has a porosity of at most 40 %.
7. Method for the production of an anode-supported fuel cell, comprising the production of an anode support with the anode and electrolyte applied thereto, application of the cathode layer thereto, followed by sintering of the assembly thus obtained, the production of the anode support comprising the provision of a green substrate, application of the anode layer and an electrolyte thereto, a stress compensation layer being applied to the substrate on the side away from the anode layer, characterised in that said stress compensation layer is applied extending uninterrupted over the substrate and after sintering an electron-conducting porous layer is applied thereto, after which the substrate and the



WO 2004/006365

PCT/NL2003/000492

7

layer applied thereto are subjected to a sintering treatment.

8. Method according to Claim 7, wherein said sintering treatment is carried out at 1300 - 1400 °C.

5



9. Method according to one of Claims 7 or 8, wherein said stress compensation layer is applied to said substrate by screen printing.

10. Method according to one of Claims 7 - 9, wherein said stress compensation layer is provided with openings having a maximum size of 1 mm extending through said layer.

WO 2004/006365

PCT/NL2003/000492

1/1

*Fig 1**Fig 2*

## INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/NL 03/00492

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 7	H01M4/86	H01M4/88 H01M8/02
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 7 H01M		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the International search (name of data base and, where practical, search terms used)		
EPO-Internal, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 01 43524 A (BUCHKREMER HANS PETER ;BLASS GUENTER (DE); MESCHKE FRANK (DE); FLE) 21 June 2001 (2001-06-21) cited in the application claim 1 page 6, line 32,33	1,7-9
A	EP 0 454 924 A (WESTINGHOUSE ELECTRIC CORP) 6 November 1991 (1991-11-06) column 5, line 40-53	1,3,7
A	DE 196 26 342 A (KERNFORSCHUNGSANLAGE JUELICH) 8 January 1998 (1998-01-08) column 3, line 53-55 column 4, line 18-21	1-10
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents:		
*A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *Z* document member of the same patent family		
Date of the actual completion of the international search		Date of making of the international search report
10 October 2003		17/10/2003
Name and mailing address of the ISA European Patent Office, P.B. 6818 Patentlaan 2 NL - 2250 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  Reich, C

Form PCT/ISA/210 (second sheet) (July 1997)

## INTERNATIONAL SEARCH REPORT

II  
International Application No  
PCT/NL 03/00492

C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 788 175 A (SULZER INNOTECH AG) 6 August 1997 (1997-08-06) the whole document	1-10

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 2 of 2

## INTERNATIONAL SEARCH REPORT

 If  
 National Application No  
 PCT/NL 03/00492

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0143524	A	21-06-2001	DE 19960674 A1	05-07-2001
			AU 2351201 A	25-06-2001
			AU 2830601 A	25-06-2001
			WO 0143524 A2	21-06-2001
			WO 0145186 A2	21-06-2001
			EP 1240681 A2	18-09-2002
EP 0454924	A	06-11-1991	US 5132352 A	21-07-1992
			CA 2032117 A1	28-10-1991
			EP 0454924 A1	06-11-1991
			JP 4237958 A	26-08-1992
			KR 170370 B1	30-03-1999
			NO 910023 A	28-10-1991
DE 19626342	A	08-01-1998	DE 19626342 A1	08-01-1998
EP 0788175	A	06-08-1997	EP 0788175 A1	06-08-1997
			AT 191815 T	15-04-2000
			AU 707763 B2	22-07-1999
			AU 1239397 A	07-08-1997
			DE 59604956 D1	18-05-2000
			DK 788175 T3	10-07-2000
			JP 9223508 A	26-08-1997
			US 5932368 A	03-08-1999

Form PCT/ISA/210 (patent family annex) (July 1992)